MedEco XGI C4

Technical Datasheet

Product description

MedEco XGI C4 is a > 99.9 % bio-based LDPE grade with optimized friction properties for the extrusion of tubing and film. Its high chemical resistance makes XGI C4 an excellent choice for catheters and primary pharmaceutical packaging.

Material properties

All values given are indicative. The data was measured on test objects and may vary due to product-specific geometry and process characteristics.

Properties	Method	Condition	Value	Unit
Density	calculated		0.94	g/cm³
MFR	ISO 1133-A	190 °C/ 2.16 kg	0.35	g/10min
Tensile strength	ISO 527-1/1A		14	N/mm²
Elongation at break	ISO 527-1/1A		75	%
Young‘s modulus	ISO 527-1/1A		200	N/mm²
Charpy impact strength	ISO 179/1eU	23 °C	> 98	kJ/m²
Charpy notched impact strength	ISO 179/1eA	23 °C	74	kJ/m²

BIOVOX GmbH | Bunsenstraße 15 | 64293 Darmstadt
be-green@biovox.systems | +49 6151 7869330
Geschäftsführer: Dr.-Ing. Julian Lotz, Dr.-Ing. Vinzenz Nienhaus, Carmen Rommel
Registergericht: Amtsgericht Darmstadt, HRB 101494

MedEco XGI C4

Technical Datasheet

Storage and drying conditions

Store the material in an airtight container in a dry, cool place. Protect it from heat, direct sunlight, sources of ignition, and moisture. Do not store it outdoors. Use the material within six months of delivery. Dry the material for at least two hours at 80 °C. Process dried MedEco XPI G4 promptly or store the material briefly in closed containers.

Packaging

The product is available in 25-kg bags or big bags. Samples are supplied in 25-kg bags. It is available worldwide.

Processing instructions

Parameter	min	max	Initial value	Unit
Periphery temperature	15	60	25	°C
Feed zone temperature	160	200	180	°C
Compression zone temperature	180	230	200	°C
Metering zone temperature	180	250	210	°C
Nozzle temperature	180	250	220	°C
Melt temperature	180	250	200	°C
Residence time in the screw	0	5	3	min

Questions?

Ask your contact or email be-green@biovox.systems

BIOVOX GmbH | Bunsenstraße 15 | 64293 Darmstadt
be-green@biovox.systems | +49 6151 7869330
Geschäftsführer: Dr.-Ing. Julian Lotz, Dr.-Ing. Vinzenz Nienhaus, Carmen Rommel
Registergericht: Amtsgericht Darmstadt, HRB 101494